



Nitrile

## Extended chemical splash protection, approved for handling chemotherapy drugs

- Superior strength and durability for maximum protection against rips, snags or tears
- Low, 0.65 AQL for advanced barrier protection
- Tested for use with chemotherapy/cytotoxic drugs
- Meets or exceeds the emergency medical glove requirements of NFPA 1999



### Industries

- Automotive
- Automotive Aftermarket
- Life Sciences
- Healthcare

### Recommended For

- Inspection, selecting, checking parts
- Assembly and inspection of components
- Picking and fastening components
- Equipment repair and maintenance
- General Purpose Auto Aftermarket
- Tire rotation & changes
- Animal care feeding and cleanup
- Maintaining lab furniture and equipment
- Sample taking and processing
- Administering drugs
- Raw material sample collection
- Tested for use with chemotherapy drugs
- Extra protection over the wrist and arm
- Higher-risk clinical applications
- Protection from Type I latex allergy in HCW's or patients



### TECHNICAL DATA SHEET

#### PRODUCT INFORMATION

	Supreno® EC SEC-375
<b>Material</b>	Nitrile
<b>Color</b>	Violet Blue
<b>Glove Design</b>	Chlorinated, Powder-Free, Textured Fingers
<b>Cuff</b>	Beaded
<b>Manufacturing/QMS Audit Standards</b>	ISO 13485:2003
<b>Regulatory/Standards Compliance</b>	Food Type: Rubber, EN 420:2003 + A1:2009, FDA21 CFR 177-2600, ISO 13485, NFPA 1999:2013, US QSR/FDA 510(k) Medical Examination Grade
<b>Packaging</b>	50 gloves per dispenser 10 dispensers per case 500 gloves per case *40 gloves per dispenser (Size XXXL) *400 gloves per case (Size XXXL)
<b>Storage</b>	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition
<b>Country of Origin</b>	Malaysia
<b>User Needs Segment</b>	High Risk
<b>Available sizes</b>	XS (5.5 - 6), S (6.5 - 7), M (7.5 - 8), L (8.5 - 9), XL (9.5 - 10), XXL (10.5 - 11), XXXL (11.5-12)

#### PHYSICAL PROPERTIES

	Typical Values		Testing Method
Length (mm/inches)	295 / 11.6		ASTM D3767,EN420
Freedom from Holes (Inspection level I)	0.65 AQL		ASTM D5151,EN 455-1
Palm Thickness (mm/inches)	0.14 / 5.5		ASTM D3767,EN420
Finger Thickness (mm/inches)	0.21 / 8.3		ASTM D3767,EN420
	<b>BEFORE AGING</b>	<b>AFTER AGING</b>	
Ultimate Tensile Strength (MPa)	30	27	ASTM D412
Elongation at Break (%)	500	500	ASTM D412
Force at break (N)	18	18	EN 455-2

For additional information visit us at [www.ansell.com](http://www.ansell.com), or call us at

##### Europe, Middle East & Africa Region

Ansell Healthcare Europe NV  
Riverside Business Park  
Blvd International, 55  
1070 Brussels, Belgium  
T: +32 (0) 2 528 74 00  
F: +32 (0) 2 528 74 01

##### Asia Pacific Region

Ansell Global Trading Center  
(Malaysia) Sdn Bhd  
Prima 6, Prima Avenue  
Block 3512, Jalan Teknokrat 6  
63000 Cyberjaya  
Selangor, Malaysia  
T: +603 8310 6688  
F: +603 8310 6699

##### North America Region

Ansell Healthcare Products LLC  
111 Wood Avenue South,  
Suite 210  
Iselin, NJ 08830, USA  
T: +1 800 800 0444  
F: +1 800 800 0445

##### Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V.  
Blvd. Bernardo Quintana No. 7001-C,  
Q7001 Torre II,  
Suites 1304, 1305 y 1306,  
Col. Centro Sur, c.p. 76079  
Queretaro, Qro. Mexico  
T: +52 442 248 1544 / 248 3133

##### Australia

Ansell Limited  
Level 3,678 Victoria Street,  
Richmond, Vic, 3121  
Australia  
T: +61 1800 337 041  
F: +61 1800 803 578

##### Russia

Ahcenn PYC  
123610 Poccnr, Mockba  
Kpachonpechehckar  
Ha6. 12, n.3, op. 1304A  
Ten. +7 495 258 13 16

**Performance Standards and Regulatory Compliance**



Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: [www.ansell.com/patentmarking](http://www.ansell.com/patentmarking) © 2019 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.